



SYNTHOS XPS



DRUCKFESTIGKEITEN:

250 kPa: 20 - 30 mm
 300 kPa: 40 - 240 mm
 500 kPa: 40 – 240 mm
 700 kPa: 40 – 200 mm

	XPS-Platten mit gewaffelt, gerade Kante	Dicke: 20 -120 mm Plattenformat: 1250x600
	XPS-Platten mit glatt, Stufenfalz	Dicke: 20 -240 mm Plattenformat: 1265x615

Stärke	[W/mK]	Stk./Pkt.	m2/Pkt.	m3/Pkt.	Pkt./Pal.	m2/Pal.	m3/Pal.
20 mm	0,032	20	15,00	0,300	12	180,00	3,60
30 mm	0,033	14	10,50	0,315	12	126,00	3,78
40 mm	0,032	10	7,50	0,300	12	90,00	3,60
50 mm	0,032	8	6,00	0,300	12	72,00	3,60
60 mm	0,032	7	5,25	0,315	12	63,00	3,78
80 mm	0,034	5	3,75	0,300	12	45,00	3,60
100 mm	0,035	4	3,00	0,300	12	36,00	3,60
120 mm	0,036	4	3,00	0,360	10	30,00	3,60
140 mm	0,034	3	2,25	0,360	12	27,00	3,78
150 mm	0,034	3	2,25	0,315	10	22,50	3,78
160 mm	0,034	3	2,25	0,338	10	22,50	3,60
170 mm	0,035	3	2,25	0,360	10	22,50	3,83
180 mm	0,035	2	1,50	0,270	14	21,00	3,78
190 mm	0,035	2	1,50	0,285	12	18,00	3,42
200 mm	0,035	2	1,50	0,300	12	18,00	3,60
210 mm	0,036	2	1,50	0,315	12	18,00	3,78
220 mm	0,036	2	1,50	0,330	10	15,00	3,30
230 mm	0,036	2	1,50	0,345	10	15,00	3,45
240 mm	0,036	2	1,50	0,360	10	15,00	3,60

